

FOLDING BLANCO

ZIBO (GC1)



ESPECIFICACIONES TÉCNICAS

	GRAMAJE (g/m ²)	ESPESOR (μm)	RIGIDEZ TABER 15° (mNm)	
			DT	DM
	210	305	3.6	6.8
	235	355	4.8	8.6
	250	380	5.8	10.8
	270	410	7.1	13.0
	300	460	9.4	17.6
	325	510	13.2	23.0
	350	560	15.0	28.4
Tolerancia	+/- 3 %	+/- 15	- 15 %	

PROPIEDADES

LISURA (ISO 8791) (pps)	≤ 1.6 μm
BLANCURA (ISO2470-2) (%)	Cara 89 Reverso 87
BRILLO 75° (ISO8254) (%)	≥40
HUMEDAD (ISO287) (%)	7 ± 1.5

1001994

Rev. 0

Abril 2022

El Fabricante del material se reserva el derecho a modificaciones sin previo aviso.