

PAPEL ESTUCADO MATE DOS CARAS



Diseñado para cualquier aplicación gráfica

ESPECIFICACIONES TÉCNICAS

	GRAMAJE (g/m²) (ISO 536)	ESPESOR (μm) (ISO 534)	LISURA BEKK (s) (ISO 5627)	OPACIDAD % (ISO 2471)
	90	80	210	92
	100	86	210	93
	115	100	220	95
	125	107	220	95,5
	130	111	220	96
	135	115	220	96
	150	131	200	97
	170	152	160	97,5
	200	181	160	–
	225	210	130	–
	250	239	120	–
	270	263	120	–
	300	299	100	–
	350	358	100	–
Tolerancia	+4%	±4%		

PROPIEDADES

BLANCURA (CIE D65/10° ISO 11475)	120 (±3%)
HUMEDAD RELATIVA (TAPPI T-502) (%)	50 (±7%)