

Cartón Kraft estucado una cara.

Mètodes d'impressió

Offset



Alimentació



Alimentació
congelats



Higiene



Packaging
genèric



Parafarmàcia



Sector agrícola



Sector Industrial

ESPECIFICACIONS TÈCNIQUES

GRAMAJE (g/m2) (T-410)	ESPESOR (µm) (T-411)	RIGIDEZ TABER 15° (mNm) (T-489)	RIGIDEZ TABER 15° (mNm) (T-489)
		DM	DT
290	356	13.7	6.9
330	406	19.6	9.8
360	457	27.0	13.7
390	508	34.3	17.2
415	559	43.1	20.6
450	610	53.4	25.0
485	660	63.7	30.4
520	711	74.5	36.3
555	762	85.3	41.7

PROPIEDADES

BLANCURA (T-452) (%)	78
----------------------	----

1231011/1211011

Junio 2025

El Fabricante del material se reserva el derecho a modificaciones sin previo aviso.
Certificado de Cadena de Custodia PEFC N° CU-PEFC-COC-821792 para poder servir este material Certificado PEFC.
Certificado de Cadena de Custodia CU-COC-821792 para poder servir este material certificado FSC, previa consulta.