

KRAFTLINER PAPER (UNCOATED)



Printing methods

Flexography
Offset



Agricultural Sector



Electronic Products



Food



Industrial Sector



Tobacco

TECHNICAL SPECIFICATIONS

WEIGHT (g/m ²) (ISO 536)	THICKNESS (mm) (ISO 534)	BURST STRENGTH (kPa) (ISO 2758)	SCT DT (KN/m) (ISO9895)
100	143	460	2.0
110	158	530	2.3
125	188	580	2.5
135	193	620	2.7
170	243	730	3.4
186	268	790	3.7
200	290	850	4.0
225	325	914	4.4
250	355	966	5.0
275	396	1050	5.4
300	437	1176	6.0
400	565	1290	7.3

PROPIEDADES

COBB 60s (g/m²) (ISO535)

DENNISON TEST (n°) (TAPPI 459 om-08)

HUMIDITY (%) (ISO 287)

feb-23

The manufacturer of the material reserves the right to make changes without prior notice. (**) Thickness values are indicative and are not guaranteed by the factory. Chain of Custody Certificate CU- SOP-821792 to be able to serve this FSC-Mix certified material.