# COMKRAFT CMPC RC (FOLDING KRAFT)

Paperboard for folding carton packaging. The combination of a middle layer of mechanical pulp and top layers of high quality ECF chemical pulp gives the paperboard an excellent stiffness for its grammage . This facilitates high and interrupted production speeds on converting and packaging lines. This facilitates high and interrupted production speeds on converting and packaging lines. Designed for high quality packaging for pharmaceutical, frozen, food and other non-food uses. Printing method: Offset, Rotogravure, Flexo.

### Printing methods

Offset
Rotogravure
Flexography


Agricultural Sector


Cleaning


Editorial


Food


Generic Packaging


Hygiene


POS Advertising

## TECHNICAL SPECIFICATIONS

| | WEIGHT ($g/m^2$) (ISO 536) | THICKNESS (mm) (ISO 534) | TABER RIGIDITY 15° (mNm) (ISO 2493) | TABER RIGIDITY 15° (mNm) |
|---|---|---|---|---|
| | | | DT | DM |
| | 180 | 280 | 2.5 | 5.5 |
| | 200 | 315 | 3.6 | 7.9 |
| | 225 | 365 | 5.1 | 11.2 |
| | 245 | 400 | 6.4 | 13.3 |
| | 255 | 432 | 7.7 | 16.0 |
| | 265 | 457 | 9.3 | 19.3 |
| | 285 | 508 | 11.8 | 24.5 |
| | 295 | 533 | 12.5 | 26.3 |
| | 310 | 559 | 14.9 | 31.3 |
| | 330 | 610 | 18.3 | 38.3 |
| | 345 | 660 | 20.6 | 43.9 |
| | 370 | 711 | 24.5 | 52.2 |

## PROPIEDADES

| | |
|---|---|
| SMOOTHNESS (TAPPI 555) (pps) | |
| WHITENESS (ISO2470) (%) | |
| HUMIDITY (TAPPI 412) (%) | |

Jan-23

The manufacturer of the material reserves the right to make changes without prior notice.
Chain of Custody Certificate CU- SOP-821792 to be able to serve this FSC certified material.