COMCOTE WOOD FOLDING (GC2)

Bleached thermo-mechanical pulp board with layers of chemical pulp that give it excellent machinability. Designed for packaging of dry and frozen foods, pharmaceutical products, cosmetics, and book covers. Printing method: Offset, Rotogravure.

Printing methods

Offset
Rotogravure
Flexography

Food

Graphics

Pharmacy

TECHNICAL SPECIFICATIONS

	WEIGHT (g/m²) (ISO 536)	THICKNESS (mm) (ISO 534)	TABER RIGIDITY 15° (mNm) (ISO 2493)	TABER RIGIDITY 15° (mNm)
			DT	DM
	215	356	4.5	9.4
	235	406	6.0	12.3
	250	432	7.4	15.4
	260	470	9.5	19.8
	275	500	11.3	24.1
	295	533	14.0	29.1
	310	559	15.5	32.2
	325	610	18.0	37.4
	370	690	23.0	51.0

PROPIEDADES

	SMOOTHNESS (TAPPI 555) (pps)
	WHITENESS (ISO2470) (%)
	GLOSS 75º (TAPPI 480) (%)
	HUMIDITY (TAPPI 412) (%)|

sept-23

The manufacturer of the material reserves the right to make changes without prior notice.
Chain of Custody Certificate CU- SOP-821792 to be able to serve this FSC certified material.