



Pasta química sin blanquear

Printing methods

Offset



Food



Food Delivery



Generic Packaging



Parapharmacy

TECHNICAL SPECIFICATIONS

GRAMAJE (g/m2) (T-410)	ESPESOR (µm) (T-411)	RIGIDEZ TABER 15° (mNm) (T-489)	RIGIDEZ TABER 15° (mNm) (T-489)
-	-	DM	DT
258	381	11.8	5.4
288	432	16.2	6.4
302	457	19.6	8.3
332	508	26.5	10.8
356	559	30.9	14.2
380	610	38.2	17.2
410	660	45.1	21.1

PROPIEDADES

COBB (2 min.) (T-441) (g/m2)	40
------------------------------	----

2477011

Junio 2025

El Fabricante del material se reserva el derecho a modificaciones sin previo aviso.
Certificado de Cadena de Custodia PEFC N° CU-PEFC-COC-821792 para poder servir este material Certificado PEFC.
Certificado de Cadena de Custodia CU-COC-821792 para poder servir este material certificado FSC, previa consulta.