

COMKRAFT CMPC RC (FOLDING KRAFT) (copia)



Paperboard for folding carton packaging. The combination of a middle layer of mechanical pulp and top layers of high quality ECF chemical pulp gives the paperboard an excellent stiffness for its grammage. This facilitates high and interrupted production speeds on converting and packaging lines. This facilitates high and interrupted production speeds on converting and packaging lines. Designed for high quality packaging for pharmaceutical, frozen, food and other non-food uses. Printing method: Offset, Rotogravure, Flexo.

Printing methods

Offset
Rotogravure
Flexography



Agricultural
Sector



Food



Food Delivery



Frozen foods



Generic
Packaging



Industrial Sector



POS Advertising

TECHNICAL SPECIFICATIONS

WEIGHT (g/m ²) (ISO 536)	THICKNESS (mm) (ISO 534)	TABER RIGIDITY 15° (mNm) (ISO 2493)	TABER RIGIDITY 15° (mNm)
		DT	DM
180	280	2.5	5.5
200	315	3.6	7.9
225	365	5.1	11.2
245	400	6.4	13.3
255	432	7.7	16.0
265	457	9.3	19.3
285	508	11.8	24.5
295	533	12.5	26.3
310	559	14.9	31.3
330	610	18.3	38.3
345	660	20.6	43.9
370	711	24.5	52.2

PROPIEDADES

SMOOTHNESS (TAPPI 555) (pps)

WHITENESS (ISO2470) (%)

HUMIDITY (TAPPI 412) (%)

Jan-23

The manufacturer of the material reserves the right to make changes without prior notice.
Chain of Custody Certificate CU- SOP-821792 to be able to serve this FSC certified material.