

DUPLEX BOARD GREY BACK (GD2)



- 
Alimentación
- 
Gráfica
- 
Higiene
- 
Limpieza
- 
Packaging genérico
- 
Productos electrónicos
- 
Sector Industrial

ESPECIFICACIONES TÉCNICAS			
GRAMAJE (g/m²) (ISO 536)	ESPESOR (µm) (ISO 534)	RIGIDEZ TABER 15° (mNm) (ISO 2493)	RIGIDEZ TABER 15° (mNm) (ISO 2493)
-	-	DM	DT
200	240±20	4.2	2.2
220	265±20	5.4	2.7
230	275±20	5.9	2.9
240	285±20	6.4	3.2
250	305±20	6.9	3.4
260	315±20	7.4	3.7
270	340±20	8.8	4.4
280	355±20	10.8	5.4
300	385±25	11.8	5.9
320	410±25	13.7	6.4
330	425±25	15.2	6.9
350	455±25	17.7	8.8
400	520±25	24.5	12.3
450	590±25	34.3	17.2
480	630±30	44.1	22.1
TOLERANCIA +/- 5%			

PROPIEDADES	
BLANCURA (ISO 7026) (%)	> 76