

CARTÓN REVERSO BLANCO (GT1) provisional

Cartón estucado fabricado con fibras recicladas y el reverso blanco.



Méthodes d'impression

- Offset
- Flexografía
- Huecograbado



Hygiène



Nettoyage



Emballage générique



Produits électroniques



Secteur industriel

CARACTÉRISTIQUES TECHNIQUES			
GRAMAJE (g/m2) (ISO 536)	ESPESOR (µm) (ISO 534)	RIGIDEZ TABER 15° (mNm) (ISO 2493)	RIGIDEZ TABER 15° (mNm) (ISO 2493)
-	-	DM	DT
250	350	8.0	4.8
275	385	10.8	5.1
300	422	13.5	5.6
325	455	17.0	6.4
350	489	20.0	7.9
375	529	24.6	9.8
400	558	29.6	12.0
425	595	35.1	13.1
450	630	41.6	15.7
TOLERANCIA	+/- 4 %	+/- 5 %	-15%

PROPIEDADES	
BLANCURA SUPERFICIE (ISO 2470-2) (%)	82 +/- 2%
BLANCURA REVERSO (ISO 2470-2) (%)	77 +/- 2%

0301012

Julio 2026

El Fabricante del material se reserva el derecho a modificaciones sin previo aviso.
Certificado de Cadena de Custodia CU-COC-821792 para poder servir este material certificado FSC.