

Cartón Kraft sin estucar.



Pasta química sin blanquear

Métodos de impresión

Offset



Alimentar



Food Delivery



Embalagens genéricas



Parafarmácia

ESPECIFICAÇÕES TÉCNICAS

GRAMAJE (g/m ²) (T-410)	ESPESOR (µm) (T-411)	RIGIDEZ TABER 15° (mNm) (T-489)	RIGIDEZ TABER 15° (mNm) (T-489)
-	-	DM	DT
258	381	11.8	5.4
288	432	16.2	6.4
302	457	19.6	8.3
332	508	26.5	10.8
356	559	30.9	14.2
380	610	38.2	17.2
410	660	45.1	21.1

PROPIEDADES

COBB (2 min.) (T-441) (g/m²)

40

2477011

Junio 2025

El Fabricante del material se reserva el derecho a modificaciones sin previo aviso.
Certificado de Cadena de Custodia PEFC N° CU-PEFC-COC-821792 para poder servir este material Certificado PEFC.
Certificado de Cadena de Custodia CU-COC-821792 para poder servir este material certificado FSC, previa consulta.