

Technical specifications



Bleached chemical pulp
Groundwood pulp



Food service

Typical technical values for PankaPlex

Property / Unit	Tolerance						Standards
Grammage, g/m ²	±5%	220	240	265	300*	350*	ISO 536
Thickness, µm	±5%	370	400	450	500	600	ISO 534
Surface Smoothness, Bendtsen, ml/min		200	200	200	200	300	ISO 8791-2
Bending moment Taber 15° MD, mNm	-15%	8.0	12.0	16.0	18.5	28.0	ISO 2493
Bending moment Taber 15° CD, mNm	-15%	4.0	5.0	6.5	8.0	11.5	

*Grammage produced upon special request only, minimum production volume 10 tonnes
PankaPlex is available only in reels

Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
Moisture, %	±1.5	9.0	ISO 287
ISO Brightness C/2°, %, Top	±1.5	76	ISO 2470-1
Scott Bond, J/m ²	> 90	100	TAPPI 569
Cobb 180 s top, g/m ²	< 60	50	ISO 535
Cobb 180 s reverse, g/m ²	< 60	50	ISO 535
pH of Aqueous Extract		7.5 – 10.0	ISO 6588
Alkali Reserve, mol/kg		> 0.4	ISO 10716

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes



Available as
carbon neutral
on request

For more information contact your
local sales representatives or

Pankakoski Mill Oy
Ruukintie 2
FI-81750 Pankakoski
Finland

Tel. +358 (0) 10 480 4600

www.pankaboard.com

Scan to find your local
Pankaboard sales contact

